

HH4765 (BL3VD)

 High Density Polyethylene for
 Small Blow Moulding

Typical Applications

- Sheet for thermoforming
- Containers
- Fabric softeners

Catalyst: THT/BM

Product Specification

PHYSICAL/MECHANICAL PROPERTIES	VALUE*	UNIT	TEST METHOD
Density	0.959±0.002	g/cm ³	ISO 1183
FRR 5/2.16	19±3		
MFR190°/2.16	28±4	g/10 min	ISO 1133
MFR190°/5	1.5±0.3	g/10 min	ISO 1133
Notched impact (23 °C)	≥7	MJ/mm ²	ISO 179/1eA

* Typical values; not to be considered as product specification.

Note:

Test specimens were taken from compression moulded sheet at 23°C.

FRR values are statistical and calculated by dividing MFR values.

Notch impact test specimen was taken from compressed moulded sheet at 23°C and the data quoted here are average values.